



## VSS EMULTECH

W. Sacramento, CA 95691  
3785 Channel Drive  
Ph: (916) 371-8480  
Fx: (916) 371-2457

Redding, CA 66001  
7200 Pit Road  
Ph: (530) 241-1364  
Fx: (530) 246-2912

Bakersfield, CA 93308  
3800 Gilmore Avenue  
Ph: (661) 323-5904  
Fx: (661) 323-2737

### Product Data Sheet Black Diamond Seal Coat

Test	Specification	Typical Result	Specification	
			min	max
Residue at 300-400 °F, wt. %	hot plate*	55.0	55	65
Solubility of residue in C <sub>2</sub> HCl <sub>3</sub> , %	AASHTO T44	17.5	15.0	20.0
Loss on ignition of insoluble residue, %	ASTM D6	6.0		16.0
Cone penetration, 77 °F, dmm	ASTM D217	450	400	700

\* place 25g sample in 1 quart can and heat at 300-400F for 15-20 minutes, weigh sample every 10 minutes until constant weight is obtained.