



VSS EMULTECH

W. Sacramento, CA 95691
3785 Channel Drive
Ph: (916) 371-8480
Fx: (916) 371-2457

Redding, CA 66001
7200 Pit Road
Ph: (530) 241-1364
Fx: (530) 246-2912

Bakersfield, CA 93308
3800 Gilmore Avenue
Ph: (661) 323-5904
Fx: (661) 323-2737

Product Data Sheet CQS-1H

Tests	Test Method	Typical Result	Specification	
			min	max
Viscosity @ 25°C, SFs	AASHTO T59	30.0	15	90
Sieve, %	AASHTO T59	0	-	0.30
Residue by Distillation, % by wt.	AASHTO T59	62	57.0	-
Storage Stability, 1 day, %	AASHTO T59	0.1	-	1.0
Particle Charge	AASHTO T59	Positive	Positive	
Tests on Residue				
Penetration @ 25°C, 100 g, 5 sec	AASHTO T49	50	40	90
Ductility @ 25°C, mm	AASHTO T51	450+	400	-
Solubility, %	AASHTO T44	99.9	97	-