



VSS EMULTECH

W. Sacramento, CA 95691
3785 Channel Drive
Ph: (916) 371-8480
Fx: (916) 371-2457

Redding, CA 66001
7200 Pit Road
Ph: (530) 241-1364
Fx: (530) 246-2912

Bakersfield, CA 93308
3800 Gilmore Avenue
Ph: (661) 323-5904
Fx: (661) 323-2737

Product Data Sheet PMCRS-2h

Tests	Typical Results	Specification	
		min	max
Viscosity @ 122°F, SFs	130.0	75	350
Sieve, %	0.04	-	0.30
Residue by Evaporation, % by wt	71	65.0	-
Settlement, 5 day (%)	1.0	-	5.0
Storage Stability, 1 day, (%)	0.1		1.0
Demulsibility, 0.8% SDSS%	65.0	40.0	
Ash Content, %	<0.1		0.2
Particle Charge	Positive pH 2.0	Positive	
Tests on Residue			
Penetration @ 77°F, 100 g, 5 sec	50	40	90
Ductility @ 77°F, cm	65+	40	-
Torsional Recovery, %	36	18	
Solubility in TCE, %	99.98	97.5	-

This product contains a minimum of 2.5% latex by weight

